## Patent Claims

- 1. An electromechanical drive or sensor element having a layer structure, which comprises
- 5 a plurality of piezoelectric ceramic layers (12a-f; 22a-d; 41a-f),
  - an electrode layer (16a-e; 26a-d) which is arranged between two mutually facing surfaces of directly adjacent plezoelectric ceramic layers, and
  - an electrical connector (18a,b; 28a,b; 58a,b) for making electrical contact with the electrode layer (16a-e, 26a-d),
  - -- in which case the connector (18a,b; 28a,b; 58a,b) is likewise arranged and is passed out between the two mutually facing surfaces of the piezoelectric ceramic layers (12a-f; 22a-d; 41a-f).
- 20 2. An electromechanical drive or sensor element having a layer structure,
  - having a plural ty of piezoelectric ceramic layers (12a-f; 2/2a-d; 41a-f),
  - in which mutually facing surfaces of directly adjacent piezoelectric ceramic layers (12a-f; 22a-d; 41a-f) are metallized by application of a metal coating,
    - -- which are joined together by means of diffusion welding,
- 30 -- so that an electrode layer (16a-e; 26a-d) is formed by the metallized surfaces,
  - --- with which contact can be made via an electrical connector (18a,b; 28a,b; 58a,b).
- 35 3. The drive or sensor element as claimed in one of claims 1 or 2, in which a groove (14a-d; 24a-d; 56a-f) is provided in at least one of the two mutually facing surfaces of the piezoelectric

And the state of t

10

15

ceramic layers (12a-f; 22a-d; 41a-f) and at least partially holds the electrical connector (18a,b; 28a,b; 58a,b).

- 5 4. The drive or sensor element as claimed in claim 3, in which the connector (18a,b; 28a,b; 58a,b) is a wire which extends beyond the surfaces of the piezoelectric ceramic layers (12a-f; 22a-d; 41a-f).
- 5. The drive or sensor element as claimed in one of claims 3 or 4 having at least three piezoelectric ceramic layers (12a-f; 22a-d; 41a-f) and at least two grooves (14a-d; 24a-d; 56a-f), in which these grooves (14a-d; 24a-d; 56a-f) are arranged offset with respect to one another and with respect to a longitudinal axis (29) of the drive or sensor element.
- 20 6. The drive or sensor element as claimed in one of claims 4 or 5 having a connector (18a,b; 28a,b; 58a,b) which is in the form of a wire and is a wire having a rippled or zigzag structure.
- The drive or sensor element as claimed in one of claims 1 to 6 having piezoelectric ceramic layers (12a-f; 22a-d; 41a-f) composed of PZT material.
- 8. The drive or sensor element as claimed in one of claims 1 to 7 having piezoelectric ceramic layers (12a-f; 22a-d; 41a-f) composed of  $PbMg_{0.308}Nb_{0.617}Ti_0/_{075}O_3$ .
- 9. The drive or sensor element as claimed in one of claims 1 to 8 having piezoelectric ceramic layers (12a-f; 22a-d; 41a-f) composed of a material having a Curie temperature of more than 400°C, for example composed of Na<sub>0.5</sub>Bi<sub>4.5</sub>Ti<sub>4</sub>O<sub>15</sub> or Bi<sub>3</sub>TiNbO<sub>9</sub>.

Annual Specific Street Street Street

ļas la

Control Start Human

12.00

5

10

15

- 10. The drive or sensor element as claimed in one of claims 1 to 9 having electrode layers (16a-e; 26a-d) composed of a metallic material having a Curie temperature of more than 400°C.
- 11. The drive or sensor element as claimed in one of claims 1 to 10 having electrode layers (16a-e; 26a-d) composed of bismuth-titanate.
- 12. The drive or sensor element as claimed in one of claims 4 to 11 having connectors (18a,b; 28a,b; 58a,b) which are in the form of wires and are composed of a metallic material having high-temperature stability at more than 250°C.
- 13. The drive or sensor element as claimed in one of claims 4 to 11 having connectors (18a,b; 28a,b; 58a,b) which are in the form of wires and are composed of a material which contains stainless steel, or of such a material which contains a nickel alloy.
- 14. A method for producing an electromechanical drive 25 or sensor element having a layer structure, which comprises the following steps:
  - production of ceramic layers (12a-f; 22a-d; 41a-f) composed of electrically active material using a method which is normal in ceramic technology, having desired dimensions and having a margin of 2-3 mm for each dimension taking account of the following mechanical machining;
- grinding the ceramic layers (12a-f; 22a-d; 41a-f) until a predetermined thickness of, for example, 0.15 to 03 mm [sic] is reached;

5


10

15

20

25

- cutting a groove (14a-d; 24a-d; 56a-f) in one face of the ceramic layers (12a-f; 22a-d; 14a-f) which is to be metallized;
- -- in which case the depth of the groove (14a-d; 24a-d; 56a-f) must be no deeper than half the thickness of the ceramic layer (12a-f; 22a-d; 41a-f) under consideration;
- coating at least one face of the ceramic layers (12a-f; 22a-d; 41a-f) with metal by applying a paste containing silver twice and subsequent heat treatment at a temperature of 800-820°C;
- applying adhesive/to the metallized surfaces of two ceramic layers (12a-f; 22a-d; 41a-f) using cellulose adhesive;
- diffusion welding of the layers to which adhesive has been applied by heat treatment at a temperature of 780-800°C and single-axis compression at a pressure of 3-5 kg/cm² over a period of 3 hours and cooling to room temperature;
- drawing in each case one connector wire (18a,b; 28a,b; 58a,b) into a groove (14a-d; 24a-d; 56a-f);
- polarization of the drive or of the sensor element by the action of an electric field on the wires (18a,b; 28a,b; 58a,b) at high temperature;
  - connection of the same poles of the drive or of the sensor element;
- checking of the desired parameters and piezoelectric characteristics of the drive or of the sensor element.
- 15. A level limit switch (70) having a drive and sensor element as claimed in one of claims 1 to 14.



limit switch (70) as claimed in 16. level The claim 15, in which the sensor element is separated from the drive by /a non-polarized ceramic layer (82d).

acceleration/ sensor (40) having 17. sensor element as claimed in one of claims 1 to 14.

South Treat and the tree to th

